

# TECHNICAL INFORMATION



*-Luggage Label / Baggage Tag-*

## PB DT-PET-03/AL01D/WG62

### PHYSICAL CHARACTERISTICS

#### Facestock

DT TC-3

Top coated direct thermal paper with good image preservation, standard sensitivity and promising resistance to fats, heat and moisture, thermal image smudging and scratching.

Basis weight ISO 536 : 65 gsm  
Caliper ISO 534 : 70 µm

PET23

A transparent polyester film.

Caliper ISO 534 : 23 µm

#### Adhesive

A general purpose emulsion acrylic permanent adhesive with good die cutting performance. The adhesive has excellent tack on all normal substrates, including non-polar surfaces, film and corrugated board.

The adhesive is compliant to ISEGA for use on labelling of food packaging materials (indirect food contact) based on European requirements (EU10/2011) with recommendations of the BfR. ISEGA has EN ISO 17025 accreditation for analytics and EN 45011 for certification.

Minimum Application Temperature: +5°C  
Product Functional Service Temperature: -20°C / +80°C

#### Liner

A super-calendered white glassine backing paper.

Basis weight ISO 536 : 58 gsm  
Caliper ISO 534 : 51 µm

### PERFORMANCE CHARACTERISTICS

Properties	Test Method	Typical values
Initial Tack on Glass	FINAT FTM9	12.0 N/25mm
Adhesion to Stainless Steel	FINAT FTM2	9.0 N/25mm (20mins)
Total Product Caliper	ISO 534	173 µm

#### Shelf life

1 year when stored at 22°C and 50% RH

DT TC-3 should be stored indoor, at temperatures between 18°C and 24°C with a relative humidity of 40% to 60%. Longer term storage at temperature over 40°C or over 60% relative humidity can lead to a reduction in image contrast. Direct sunlight, fluorescent and similar UV light sources should be avoided.

The information given above are based on typical measured values; they are subject to technical changes and improvements without prior notice. It is the user's responsibility to check, prior to use, whether the product is suitable for the intended application.