

TECHNICAL INFORMATION



-Luggage Label-

PB DT-PET-03/PR80L/WG62

PHYSICAL CHARACTERISTICS

Facestock

DT TC-3

Top coated direct thermal paper with good image preservation, standard sensitivity and promising resistance to fats, heat and moisture, thermal image smudging and scratching.

Basis weight ISO 536 : 65 gsm
Caliper ISO 534 : 70 µm

PET23

A transparent polyester film.

Caliper ISO 534 : 23 µm

Adhesive

Hotmelt pressure sensitive adhesive, permanent type, with universal adhesion properties to various substrates and excellent die cutting properties. Meets composition requirements of indirect food additives regulation FDA 21-CFR-175.105.

Application Temperature : -10 °C
Product Functional Service Temperature: -30°C / +60°C

Liner

A super-calendered white glassine backing paper.

Basis weight ISO 536 : 58 gsm
Caliper ISO 534 : 51 µm

PERFORMANCE CHARACTERISTICS

Properties	Test Method	Typical values
Initial Tack on Glass	FINAT FTM9	18.0 N/25mm
Adhesion to Stainless Steel	FINAT FTM2	9.0 N/25mm (20mins)
Total Product Caliper	ISO 534	172 µm

Shelf life

1 year when stored at 22°C and 50% RH

DT TC-3 should be stored indoors, at temperatures between 18°C and 24°C with a relative humidity of 40% to 60%. Longer-term storage at temperature over 40°C or over 60% relative humidity can lead to a reduction in image contrast. Direct sunlight, fluorescent and similar UV light sources should be avoided.

The information given above are based on typical measured values; they are subject to technical changes and improvements without prior notice. It is the user's responsibility to check, prior to use, whether the product is suitable for the intended application.

Code: Y12012018
Rev03